

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(43) International Publication Date
21 October 2004 (21.10.2004)

PCT

(10) International Publication Number
WO 2004/090053 A1

- (51) International Patent Classification⁷: **C09D 5/24**, 7/12 (74) Agent: RENKEMA, J.; DSM Intellectual Property, P.O. Box 9, NL-6160 MA Geleen (NL).
- (21) International Application Number: PCT/NL2004/000223 (81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 5 April 2004 (05.04.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2003-106096 10 April 2003 (10.04.2003) JP
- (71) Applicants (*for all designated States except US*): DSM IP ASSETS B.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL). JSR CORPORATION [JP/JP]; 5-6-10, Tsukiji Chuo-ku, Tokyo 104-8410 (JP). JAPAN FINE COATINGS CO., LTD. [JP/JP]; 5-6-10, Tsukiji Chuo-ku, Tokyo 104-0045 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): YAMAGUCHI, Yoshikazu [JP/JP]; 336-20, Sakura-Machi, Yokkaichi 512-1211 (JP). ITAI, Shingo [JP/JP]; 5-6-10, Tsukiji Chuo-ku, Tokyo 104-8410 (JP). UEDA, Jiro [JP/JP]; 2-13-28-213, Kawaguchi, Tsuchiura 300-0033 (JP). TANABE, Takayoshi [JP/JP]; 2-18-33-M2-1, Umezono, Tsukuba 305-0045 (JP). SOUTHWELL, John, Edmond [US/US]; 735 Pleasant Street, Elgin 60137 (US).
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: CURABLE LIQUID COMPOSITOIN, CURED FILM, AND ANTISTATIC LAMINATE

(57) Abstract: To provide a curable liquid composition excelling in storage stability and curability and capable of forming a coat (film) which excels in antistatic properties, hardness, scratch resistance, and transparency on the surface of various substrates, a cured film of the composition, and an antistatic laminate. A curable liquid composition comprising (A) particles including an oxide of at least one element selected from the group consisting of indium, antimony, zinc, and tin as a major component, (B) a compound having at least two polymerizable unsaturated groups in the molecule, (C) a solvent in which solubility of the component (B) is less than 10 wt%, and (D) a solvent in which solubility of the component (B) is 10 wt% or more, the components (A) and (B) being uniformly dispersed or dissolved in the composition.



WO 2004/090053 A1